

TECHNICAL SHEET

| Article | | |
|---|------------------------|---|
| ANTIC | | |
| Raw material : SA Average size : 4,40 m ² Thickness : 0,8-1,0 mm Description : two tone antique effect, brilliant finish. | | |
| PROPERTY | TEST METHOD | REQUIREMENT |
| 1. Thickness | ISO 2589 | 0,8 - 1,0 mm |
| 2. Tensile strength | ISO 3376 | ≥ 10 N / mm ² |
| 3. Elongation at break | ISO 3376 | 40 – 70 % |
| 4. Tear strength | ISO 3377-1 | ≥ 20 N |
| 5. Flexing endurance (after 20.000 flex) | ISO 5402 | No damage |
| 6. Colour fastness to artificial light (Xenotest) 72 hours | ISO 105B02 | ≥ 4 blue scale |
| 7. Colour fastness to rubbing N° 500 dry rubs N° 80 wet rubs | ISO 11640 ISO 11640 | ≥ 4 grey scale ≥ 4 grey scale |
| 8. Fire resistance | F.M.V.S.S. 302 | Autoextinguishing without flame propagation |

| CHEMICAL ANALYSIS | | |
|---|----------|-------------|
| PROPERTY | TEST | REQUIREMENT |
| Chrome contents as Cr ₂ O ₃) | IUC 8 | > 3,5% |
| Solubility in dichloromethane (Fats and other solvents) | ISO 4048 | < 9% |
| Ph of aqueous extracts | ISO 4045 | > / = 3,5 |

Approved by
Duma Laboratory

